




## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 7 : <b>B21B 1/46</b>	<b>A1</b>	(11) International Publication Number: <b>WO 00/51755</b> (43) International Publication Date: 8 September 2000 (08.09.00)
<p>(21) International Application Number: PCT/KR99/00102</p> <p>(22) International Filing Date: 4 March 1999 (04.03.99)</p> <p>(71) Applicant (for all designated States except US): POHANG IRON &amp; STEEL CO., LTD. [KR/KR]; 1, Koedong-dong, Nam-ku, Pohang-shi, Kyungbuk 790-785 (KR).</p> <p>(72) Inventors; and (75) Inventors/Applicants (for US only): CHE, Deung-Mo [KR/KR]; Kwangyang Jaecholso Nae, 700, Keumho-dong, Dongkwangyang-shi, Jeollanam-do 545-090 (KR). LEE, Sang-II [KR/KR]; Kwangyang Jaecholso Nae, 700, Keumho-dong, Dongkwangyang-shi, Jeollanam-do 545-090 (KR). MIN, Yeoung-Rin [KR/KR]; Kwangyang Jaecholso Nae, 700, Keumho-dong, Dongkwangyang-shi, Jeollanam-do 545-090 (KR).</p> <p>(74) Agent: SONG, Man-Ho; 702, Teheran Bd., 825-33 Yok-sam-dong, Kangnam-gu, Seoul 135-080 (KR).</p>		<p>(81) Designated States: CN, ID, IN, US.</p> <p><b>Published</b> With international search report.</p>

(54) Title: METHOD OF MANUFACTURING HOT ROLLED STEEL SHEET USING MINI MILL PROCESS



## (57) Abstract

Disclosed is a method for manufacturing hot rolled steel sheets. The method includes the steps of passing molten steel through a continuous caster (11) having a mold after having been passed through a ladle (91) and a tundish (92) to manufacture a slab; cutting the slab to predetermined lengths using a cutter (14a) to form a plurality of cut slabs; heating the cut slabs to a predetermined temperature in a first heating furnace (15a) descaling the cut slabs heated in the first heating furnace; rolling the slabs in a reduction unit (13) to a predetermined thickness to form a plurality of flat bars; heating the flat bars to a predetermined temperature in a second heating furnace (15b); coiling the flat bars by a coiling station (16a) while the flat bars are maintained in a heated state; uncoiling the flat bars by an uncoiler (16b); and rolling the flat bars to a predetermined thickness in a finishing mill.